

Time Gloss Timeal Plus

TA-38001

Description

A high-quality, glossy final oil paint based on modified alkyd resins. It is characterized by superior leveling properties and high durability, in addition to excellent resistance to water and humidity.

Recommended Use

It is used for interior and exterior applications on concrete, cement, gypsum, wood, iron and clay surfaces, for doors, windows and cabinets, and can be used in high-use areas such as commercial buildings, hospitals, schools,

Characteristics

- Good resistance to weather conditions
- Excellent resistance to water and moisture
- Excellent washability with water and easy to remove stains
- Very good hardness and high durability
- Very good gloss stability
- Excellent softness and coverage
- Resistant to edge adhesion
- Superior adhesion strength
- Lead free

Time Gloss Timeal Plus

TA-38001

Physical Constants

Appearance	shiny.	-
Color	produced in white and according to the approved colors in the Time Paints color catalogue	-
Shine	Above 85 at 600 angle	ASTM D-523
Specific gravity	1.12	ASTM D-1475
Viscosity	90 Krebs units	ASTM D-562
Solid volume	46.30%	ASTM D-5201
Layer thickness	The suggested thickness of the dry layer is 30 microns per layer	-
Diffusion rate	The theoretical diffusion rate is 15.43 m ² /L, at a dry layer thickness of 30 microns.	-
Coverage rate	Above 95% at a thickness of 100 microns wet layer	-
Bleeding point	150 microns	ASTM D-4400
Hardness	Pass	ASTM D-3363
Scratch resistance	Pass	ASTM D-5178
Bending	Pass	ASTM D-522
Adhesion strength	Pass	ASTM D-3359
Water resistance	Pass	ASTM D-870
Flash point	38°C	-

Time Gloss Timeal Plus

TA-38001

Application Tools

- **Air spraying:**
 - Nozzle opening: (0.15 – 0.19) inches
 - Pressure on the nozzle: (15) MPa * (2100) psi
 - Spray angle: (40-60)°
- **Pneumatic spraying:**
 - Suggested nozzle size (1.5 – 1.8) mm.
- **Roller:**
 - Soft Roller: (Required type: Nardin Decor 8009-Code: 1093)
- **Brush:**
 - The appropriate type.

Thinner

"Time Thinner 504"

Thinning Ratio

(0 - 10)% by volume, when using an airless spray gun
(20 - 25)% by volume, when using air spraying
(10 - 15)% by size, for roller and brush
It depends on the weather conditions when used

Painting System

Residential Painting:

- Apply a layer of "Time Sealerin".
- Apply two coats of "Time Putty".
- Apply two coats of "Time Gloss Timeal Plus".

Iron surface coating system:

- Apply one or two layers of "Zinc Phosphate Primer" or "Time R.o Primer" taking into account the necessary drying time before applying the next layer.
- Apply two layers of "Time Gloss Timeal Plus" final paint, taking into account the necessary drying time before applying the next layer

Time Gloss Timeal Plus

TA-38001

Drying Time

- Surface drying : 3 hours
- Complete dryness : 7 days
- Hard dry : 16 hours
- Recoating Interval : 24 hours (minimum)

Previous results under ASTM D-5895

Packing

- A gallon of 3.65 litres.
- 18 liter barrel.
- Gallon: based on 3 litres. (Pace colors using a coloring machine).
- Barrel: basically 17 litres. (Pace colors using a coloring machine).

Shelf Life & Storage

In sealed container: 24 months in dry, cool and well ventilated place.

Safety Precaution

- Please read and follow the precautionary notices displayed on the container, and all caution statements on the MSDS of this product.
- Handle with care before and during use.
- During application of paint, contact of liquid paint with eyes, skin, inhalation of paint mist and paint vapour, should be strongly avoided.
- Recommended to use the product in well-ventilated area when applying the paint in insufficient ventilated areas, forced ventilation should be provided.
- Keep away from the reach of children.

For environmental safety : please donate the leftover paint and packaging to your local authorized institution for usage or recycling purpose.

Time Gloss Timeal Plus

TA-38001

Disclaimer

To the best of our knowledge the technical data listed herein is true and accurate up to publication date and is subject to change without prior notice. User must contact Al-Daman Building Materials Company to verify of any modifications before specifying or ordering the product. Thus, information given in this sheet is not intended to be exhaustive and any person using the product other than the recommendations in this sheet or without reverting to our Timepaints TSD, he should take his accountability in this connection.

As we are not capable to control the quality and the substrate's conditions as well as the factors that affect on using, or applying the product, so we never give any written or implied guarantee in these documents, but we guarantee our products to conform to Timepaints quality while we assume no responsibility for coverage, performance or injuries resulting from application. Liability "if any" is limited to replace the products mentioned above.